

NBR taiga

Acrylnitrile-butadiene-rubber, black

- NBR for low temperature applications
- Resistant to mineral oil, HFC and cold water
- Applicable for Rod and Piston seals, Wiper Seals, Rotary Seals and Static Seals

Properties	Value	Unit	DIN Standard
Hardness	82 ±5	Shore A	DIN ISO 7619-1
Density	1,293	g/cm ³	DIN EN ISO 1183-1
100% Modulus	12,2	MPa	DIN 53504
Elongation at break	147	%	DIN 53504
Tensile strength	16,3	MPa	DIN 53504
Compression set 23°C/70h	7,7	%	DIN ISO 815-1
Compression set 70°C/22h	9,9	%	DIN ISO 815-1
Compression set 100°C/22h	13,7	%	DIN ISO 815-1
Rebound resilience	45	%	DIN ISO 4662:2017
Tear resistance	4,5	N/mm	DIN ISO 34-1 A
Abrasion resistance	79	mm ³	DIN ISO 4649 B
min. Service temperature	-50	°C	
max. Service temperature	+105	°C	

All above stated data result from random tests which were taken from the ongoing production. All data were established based on standard test-specimen according to ISO, DIN and ASTM standards and can basically not be carried over to the construction element.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.